

TECHNICAL DATA – 1 of 1

MaxiForm F17

Formwork

TECHNICAL PROPERTIES

Sizes Available	2400 x 1220 17mm
Construction	17mm nominal thickness 11 plies, 1.7m face veneer
Edge Seal	Edges are sealed with 2 layer acrylic paint
Environmental	Legally sourced plantation wood, FSC
Test Results	AS 6669:2016
Film Density	Black on 2 Faces 40/135GSM
Stress Grade	F17
Density	±710kg/m ³
Timber Species	Mixed Hardwood, Eucalypt core (±80%) Acacia Faces (±20%)
Moisture Content	As per AS/NZS 2269 (not less than 6% or more than 12%)
Tolerances	As per AS/NZS 2369
Adhesives	Phenolic Glue, Type A Bond
Off-form Finish	Class 2 (1st pour, single use) and class 3
Emissions	Super E0

TRANSPORT

- Protect the panels from contact with water and direct sunlight
- Store on leveled ground to avoid deflection
- Do not move the pallet after removing the strapping

HANDLING AND STORAGE

Store on a hard, flat surface, avoiding direct contact with the ground and in a dry environment protected from water. Sudden changes in these conditions can affect the properties of the board.

AFTER USE

- Clean the plywood panels with warm water immediately after use
- Use soapy water to degrease the surface before applying release agent again
- To avoid damage to the surface, use plastic or nylon tools.